

INDUSTRY SOLUTIONS.

> SCIENCE & SERVICE SOLUTIONS.



AF 1316 16% silicone antifoam

Introduction

This antifoam is a highly active silicone emulsion based on activated polydimethylsiloxane. It has been specially formulated to prevent, control or destroy foam in liquid systems.

Key features

- High defoaming activity
- · Easily dissolved in water
- Resists to different pH values
- Resists to temperature < 70 °C

Properties*

Appearance: **Milky Liquid** Solids Content: **16** % Active Content: **10** % Specific Gravity, g/cm³: **0.98** Suitable Diluents: **Water** * The details are merely typical properties not specifications.

Applications

This antifoam can be used in textile industry for processes such as:

- water treatment
- printing
- finishing

In chemical industry it is applied to knock down as to prevent foam for the production of:

- effluent treatment (not biologic treatment)
- textile industry (printing, cleaning)
- printing inks
- · chemicals and detergents

CHT ITALIA S.R.L. Via Luigi Settembrini 9 20020 Lainate (MI) Italy

Phone +39 02 93195111 Fax +39 02 93195112

www.chtitalia.it info.italia@cht.com

Registro Imprese di Milano Cod. Fiscale e partita IVA IT00761610161

Capitale Sociale: € 3.500.000 i.v. Società unipersonale soggetta a direzione e coordinamento di RB BEITLICH INDUSTRIE-BETEILIGUNGEN GMBH

1 of 2



AF 1316 can be used either as supplied or diluted with water to the desired concentration, depending on the characteristics of the system i.e. temperature, pH, volume of foaming/foamable liquor, degree of agitation, composition and dosing system available.

The diluted product should be used within 12 hours from preparation, as the dilution is not stable without the addition of appropriate thickeners (acrylic or cellulose). All equipment used should be thoroughly cleaned before refilling with diluted product and to prevent contamination by micro-organism, the container should be closed after usage. It is possible to add to dilution water an appropriate preservative. If the diluted antifoam is separated it is recommended to gently stir the emulsion to homogenize the system.

The concentration required for good foam control depends on the process where it is employed. If there is no previous experience of a foam problem, it is generally suggested to start with a concentration of 50 ppm of active silicone and then to adjust the amount upwards or downwards in order to determine the most cost-effective concentration.

Packages

CHT Italia antifoams are available in a variety of packaging and sizes including drums and IBC's. Please contact our sales department for more information.

Health and Safety

Material Safety Data Sheets available on request.

Storage and Shelf Life

Over 12 months. This product should be stored between 5 and 30°C in clean sealed containers. The product should not be allowed to freeze.

Revision date: 05.07.2019

The information and recommendations in this publication are to the best of our knowledge reliable. However nothing herein is to be construed as a warranty or representation. Users should make their own tests to determine the applicability of such information or the suitability of any products for their own particular purposes. Statements concerning the use of the products described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is to be assumed.