

EM 1065

Introduction

Emulsion EM1065 is a water dilutable 60% silicone fluid emulsion, employed as a releasing agent for rubber and generally plastic materials. In art graphic industry it is mainly used as antistatic and slip agent, it confers resistance to scratching during paper folding processes and protection to mechanical components.

Features and Benefits

- General purpose release agent
- Minimum build-up on mould
- Moulded parts not discoloured
- Good dilution stability
- Good lubricant and antistatic properties
- Chemically inert

Applications

Emulsion EM 1065 has been formulated specially as a release agent and lubricant in a wide range of applications and processes such as:

- mould release agent
- release agent for bandaging of rubber tubes in vulcanisation process
- textile lubricant for yarn and thread as well as hosiery manufacture
- lubricant and antistatic in rotogravure off-set printing
- release agent for plastic tubes used to form bags and sacks
- gloss, slip and wettability in detergent and cleaner formulations

CHT ITALIA S.R.L.
Via Luigi Settembrini 9
20020 Lainate (MI)
Italy

Phone +39 02 93195111
Fax +39 02 93195112

www.chtitalia.it
info.italia@cht.com

Registro Imprese di Milano
Cod. Fiscale e partita IVA
IT00761610161

Capitale Sociale:
€ 3.500.000 i.v.
Società unipersonale soggetta
a direzione e coordinamento di
RB BEITLICH INDUSTRIE-
BETEILIGUNGEN GMBH

How to Use

Emulsion EM 1065 can be used either as supplied or diluted with water to the desired concentration, depending on the characteristics of the release and lubricant properties desired. Dilutions of emulsion are stable, if the diluted emulsion is separated it is recommended to gently stir the emulsion to homogenize the system. Concentration of EM 1065 required for good release and lubricant properties depends on the process where it is employed. If there is no previous experience of a foam problem, it is generally suggested to start with a dilution of 1 part of Emulsion EM 1065 to 50 parts cold water and then to adjust the amount upwards or downwards in order to determine the most cost-effective concentration. In the graphic industry dilution required is usually 1:20 but this can vary depending on the kind of paper used.

Property*	Value
appearance:	liquid
colour:	milky white
solids content:	65 ± 2 %
active content:	60 %
emulsifier type:	non-ionic
base fluid viscosity:	350 mm ² /s
density @25 °C:	approx. 0.98 g/mL
pH:	6.5 – 8.5
suitable diluents:	water

* The details are merely typical properties not specifications.

Health and Safety

Available on request

Packages

100 - 200 kg drums; IBC 1000 kg.

Shelf Life

Over 12 months. This product should be stored between 5 and 30 °C in clean sealed containers. The product should not be allowed to freeze.

The information and recommendations in this publication are to the best of our knowledge reliable. However nothing herein is to be construed as a warranty or representation. Users should make their own tests to determine the applicability of such information or the suitability of any products for their own particular purposes. Statements concerning the use of the products described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is to be assumed.