

AS1800

1 Part RTV silicone adhesive sealant paste non corrosive

Introduction

This is a non-corrosive, neutral cure, 1-part, RTV (Room Temperature Vulcanising) silicone adhesive sealant. It is one in a range of Acetone cure products which are solvent free. It exhibits excellent primerless adhesion to many substrates and cures rapidly at room temperature when in contact with atmospheric moisture to form a tough rubber. This product will not corrode copper or its alloys and is suitable for use with electronic components.

Key Features

- Non-corrosive
- Good spreading and tooling properties
- Fast skinning
- Good adhesion to most substrates

Use and Cure Information

This product is a ready for use 1 Part system. If supplied in cartridges it can be applied using either manual or pneumatic dispensing guns. It can also be applied from bulk containers using conventional drum dispensing equipment.

All surfaces to which the sealant is to be applied should be clean, dry and free from grease, dirt, and loose material. Priming of surfaces is not normally required. If using as an adhesive, it should be applied to one clean surface and the other clean surface brought into contact with it within the tack free time stated opposite. For optimum bond strength, the thickness of the sealant joint should be a minimum of 1 mm.

The sealant will cure upon exposure to atmospheric moisture, ideally between 20 to 30 °C and 40% to 70% Relative Humidity. Time taken for cure will depend on the thickness of the joint, humidity and temperature. Joints should be left undisturbed for at least 24 hours, but preferably longer to effect sufficient depth of cure. Full cure requires 7 days.

"For pneumatic dispensing of 310 ml cartridges, the recommended pressure is 2.25 to 3.45 bar (40 to 50 psi). Dispensing pressure above the recommended limits may lead to gas bypassing the piston, causing spluttering at the nozzle and poor bead quality"

Health and Safety

Safety Data Sheets available on request.

Packaging

CHT Adhesives are available in a variety of packaging including cartridges and bulk containers. Please contact our sales department for more information.

Revision Date : 02/11/2017

Download Date : 09/08/2020

Property	Test Method	Value
Uncured product		
Appearance		Thixotropic paste
Cure Type		Acetone
Extrusion Rate g/min		169 g/min
FDA	CFR (21) 177.2600	No
Max Cure Hrs @ 25 °C		24 hrs
Rheology		Paste
Self Bonding		Yes
Tack Free Time mins		2 mins
Cured product		
After 7 days cure at 23° +/-2 °C and 50+/-5% humidity		
CTE Linear ppm/°C		294 ppm/°C
CTE Volumetric ppm/°C		883 ppm/°C
Colour		White
Duro Shore A	ASTM D 2240-95	35
Elongation %	ISO 37	388 %
Linear Shrinkage %		0.5 %
Max Working Temp +°C	AFS_1540B	220 °C
Min Working Temp - °C		-50 °C
Modulus @ 100% Strain MPa		0.8 MPa
Modulus Youngs MPa		0.5 MPa
SG	BS ISO 2781	1.06
Tear kN/m	BS ISO 34-1	6 kN/m
Tensile MPa	ISO 37	2.2 MPa
Thermal Conductivity W/mK		0.2 W/mK
UL 94V-0		No
Storage		
Max storage temperature °C		40 °C
Shelf life		9 mths
Electrical properties		
Dielectric Constant @ 1kHz	ASTM D-150	2.97
Dielectric Strength kV/mm	ASTM D-149	>20 kV/mm
Dissipation Factor @ 1kHz	ASTM D-150	0.0025
Surface Resistivity ohms	ASTM D-257	3.30E+12 ohms
Volume Resistivity ohms cm	ASTM D-257	5.30E+15 ohms cm
Adhesion testing		
Lap Shear Aluminium kg/cm ²	ASTM D1002	9.22 kg/cm²
Lap Shear Copper kg/cm ²	ASTM D1002	8.1 kg/cm²
Lap Shear Stainless Steel 304 kg/cm ²	ASTM D1002	5.49 kg/cm²

The information and recommendations in this publication are to the best of our knowledge reliable. However, nothing herein is to be construed as warranty or representation. Users should make their own test to determine the applicability of such information or the suitability of any products for their own particular purposes. Statements concerning the user of the products described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is to be assumed. All values are typical and should not be accepted as a specification