

## ALPA-SIL 18101 2 part Silicone Moulding Rubber

### Description

Notch-resistant, condensation crosslinking silicone filling compound particularly for casting polyester resin.

### Key Features

- Good flowing behaviour
- Very good elastic properties
- Outstanding stability to polyester resins
- Suitable for block moulds and skin moulds with strong undercuts

### Application

casting polyester resin, printing pads, block moulds and skin moulds with strong undercuts

### Use and Cure Information

**Stir up components A and B well before processing!**

KÖRAFORM B 132 is added to ALPA-SIL 18101 at a mixing ratio of 100 : 3 according to weight and mixed with the spatula or stirring unit until the mass is homogeneous. With this mixing process, the potlife starts by which time ALPA-SIL 18101 has to be processed (casting or painting with the brush). Demoulding can be done after 18 hours. For an absolutely bubble-free vulcanisate the mixed silicone must be degassed using vacuum prior to the casting process (max. 5 minutes at 10 - 20 mbar). When moulding difficult substrates such as glass, the separation behaviour has to be verified in own tests and perhaps by adding a silicone-free separation agent.

### Solvents and cleaning agents

For removing fresh mass KÖRASOLV GL must be applied. Residues in the stirring or casting vessel can be easily removed by letting them cure in order to scrape them off afterwards.

### Property

#### Uncured Product

Property	Test Method	Value
Appearance		Translucent
Color A		Translucent
Cure Type		Condensation
De-mould Time / Full Cure at 23°C/73°F		18 h hrs
Density A	DIN 53 479	1.09
Density B	DIN 53 479	1.04
Mix Ratio By Weight		100:3
Pot Life mins at 23°C/73°F		100 mins
Viscosity A	Brookfield HBTD	30000 cP
Viscosity B	Brookfield HBTD	20 cP
Viscosity Mixed	Brookfield HBTD	29000 cP

#### Cured Product

**Standard climate DIN 50 014 - 23/50-2. Vulcanizate tested after 7 days at room temperature**

Property	Test Method	Value
Color		Transparent
Elongation at Break	DIN 53 504, S 3 A	350 %
Hardness Shore A	DIN 53 505	18
Linear Shrinkage (%)		0.5 %
Tear Resistance (N/mm)	ASTM D 624, Die B	17 N/mm / 97 ppi
Tensile Strength	DIN 53 504, S 3 A	3,5 N/mm2 / 435 psi

#### Storage

Max Storage Temperature	30 °C / 86 °F
Min Storage Temperature	5 °C / 41 °F
Shelf Life	9 mths

The content set out in the technical data sheet does not contain information upon which you should rely. It is provided for general information purposes only and does not constitute a product specification. You must obtain professional or specialist advice before taking any action based on the information provided in the technical data sheet. CHT make reasonable efforts to ensure that information set out in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or guarantees (whether express or implied) that information set out in the technical data sheet is complete, accurate, or up-to-date or that the product will be suitable for your requirements. You should carry out your own testing to determine the applicability of such information and whether the product will be suitable. CHT reserve the right to modify the technical data sheet at any time. The CHT technical service department is available to offer further information and advice and should it be needed to look at modifying current products or custom formulate a new one to meet your specific requirements. Please contact the technical service department.

**CHT Germany GmbH:** Postfach 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany  
Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, Homepage: www.cht.com / www.cht-silicones.com

	ALPA-SIL 18101 Component A	KÖRAFORM B 132 Component B		
Colour	transparent	colourless/yellowish		
Viscosity	30,000	20	mPa·s	Brookfield HBTD <sup>1)</sup>
Density	1.09	1.04	g/cm <sup>3</sup>	DIN 53 479 <sup>1)</sup>
	<b>Mixture</b>			Brookfield HBTD <sup>1)</sup>
Mixing ratio	100 : 3		according to weight	
Viscosity	29,000		mPa·s	
Potlife	100		minutes	
Demouldable after	18		hours	
	<b>Vulcanisate</b>			DIN 53 505 <sup>2)</sup> DIN 53 504 S 3 A <sup>2)</sup> DIN 53 504 S 3 A <sup>2)</sup> ASTM D 624 'Form B <sup>2)</sup> after 7 days
Hardness Shore A	18			
Tear strength	3.5		N/mm <sup>2</sup>	
Elongation at break	350		%	
Tear propagation resistance	17		N/mm	
Linear shrinking	0.5		%	
<sup>1</sup> = Measured under standard climate DIN 50 014-23/50-2				
<sup>2</sup> = Vulcanisate, measured after 7 days of storage at room temperature				

#### Storage

ALPA-SIL 18101 can be optimally processed for at least nine months if stored between 5°C and 30°C in tightly closed containers.

KOERFOARM B 132 can be optimally processed for at least six months if stored between 5 °C and 30 °C in tightly closed containers.

#### Health & Safety

##### Safety

Please observe our EC safety data sheets and the safety remarks on our container labels when handling our products. The dangerous goods regulations and the accident prevention regulations of the professional associations must be particularly observed. Keep the EC safety data sheet of the applied product at hand since it provides you with useful instructions for the safe use and disposal of the product as well as for actions to be taken in case of accidents.

#### Delivery units

ALPA-SIL 18101: 22 kg hobbocks

KÖRAFORM B 132: 0.5 kg PET bottles

Revision Date 27 Mar 2024

Revision No 2

Download Date 26 Apr 2024

The content set out in the technical data sheet does not contain information upon which you should rely. It is provided for general information purposes only and does not constitute a product specification. You must obtain professional or specialist advice before taking any action based on the information provided in the technical data sheet. CHT make reasonable efforts to ensure that information set out in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or guarantees (whether express or implied) that information set out in the technical data sheet is complete, accurate, or up-to-date or that the product will be suitable for your requirements. You should carry out your own testing to determine the applicability of such information and whether the product will be suitable. CHT reserve the right to modify the technical data sheet at any time. The CHT technical service department is available to offer further information and advice and should it be needed to look at modifying current products or custom formulate a new one to meet your specific requirements. Please contact the technical service department.

**CHT Germany GmbH:** Postfach 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany  
Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, Homepage: www.cht.com / www.cht-silicones.com