

## KÖRAFORM K 12 2 part casting compound

Description	Property	Test Method	Value
Notch-resistant, condensation crosslinking silicone filling compound	<b>Uncured Product</b>		
<b>Key Features</b>	Color A		White
<ul style="list-style-type: none"> <li>Very good flowing behaviour</li> <li>Is convincing through the accurate reproducibility of the moulding</li> <li>Very good elastic properties</li> <li>Low hardness Shore A</li> </ul>	Color B		Colourless / yellowish
<b>Use and Cure Information</b>	Cure Type		Condensation
Stir up KÖRAFORM K 12 well before processing so that any deposited filling substances are homogeneously distributed. KÖRAFORM B 132 is added to KÖRAFORM K 12 at a mixing ratio of 3 : 100 according to weight and mixed with the spatula or stirring unit until the mass is homogeneous. With this mixing process, the potlife starts by which time KÖRAFORM K 12 has to be processed (casting or painting with the brush). Demoulding can be done after 20 hours. For an absolutely bubble-free vulcanisate the mixed silicone gel must be degassed using vacuum prior to the casting process (max. 5 minutes at 10 - 20 mbar). By adding up to 1 weight percent of KÖRAFORM TM C to the catalysed mass, the viscosity can be increased up to stability. When moulding difficult substrates such as glass, the separation behaviour has to be verified in own tests and perhaps by adding a silicone-free separation agent.	De-mould Time / Full Cure at 23°C/73°F		20 hrs
	Density A	DIN 53 479	1.08
	Density B	DIN 53 479	1.04
	Mix Ratio By Weight		100:3
	Pot Life mins at 23°C/73°F		90 mins
	Viscosity A	Brookfield HBTD	14000 cP
	Viscosity B	Brookfield HBTD	20 cP
	Viscosity Mixed	Brookfield HBTD	13500 cP
	<b>Cured Product</b>		
	<b>Standard climate DIN 50 014 - 23/50-2. Vulcanizate tested after 7 days at room temperature</b>		
	Color		White/yellowish
	Elongation at Break	DIN 53 504, S 3 A	380 %
	Hardness Shore A	DIN 53 505	12
	Linear Shrinkage (%)		0.5 %
	Tear Resistance (N/mm)	ASTM D 624, Die B	380 N/mm / 2170 ppi
	Tensile Strength	DIN 53 504, S 3 A	2.40 N/mm <sup>2</sup> / 348 psi
	<b>Storage</b>		
	Max Storage Temperature		30 °C / 86 °F
	Min Storage Temperature		5 °C / 41 °F
	Shelf Life		9 mths

### Storage

KÖRAFORM K 12 can be optimally processed for at least nine months if stored between 5 °C and 30 °C in tightly closed original containers.  
KÖRAFORM B 132 can be optimally processed for at least six months if stored between 5 °C and 30 °C in tightly closed original containers.

### Health & Safety

#### Safety

Please observe our safety data sheets and the safety remarks on our container labels when handling our products. The dangerous goods regulations and the accident prevention regulations of the professional associations must be particularly observed. Keep the safety data sheet of the applied product at hand since it provides you with useful instructions for the safe use and disposal of the product as well as for actions to be taken in case of accidents.

#### Delivery units

KÖRAFORM K 12: 22 kg hobbocks or 220 kg drums  
KÖRAFORM B 132: 0.5 kg PET bottles

Revision Date 16 Jan 2024  
Revision No 3  
Download Date 24 Apr 2024

The content set out in the technical data sheet does not contain information upon which you should rely. It is provided for general information purposes only and does not constitute a product specification. You must obtain professional or specialist advice before taking any action based on the information provided in the technical data sheet. CHT make reasonable efforts to ensure that information set out in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or guarantees (whether express or implied) that information set out in the technical data sheet is complete, accurate, or up-to-date or that the product will be suitable for your requirements. You should carry out your own testing to determine the applicability of such information and whether the product will be suitable. CHT reserve the right to modify the technical data sheet at any time. The CHT technical service department is available to offer further information and advice and should it be needed to look at modifying current products or custom formulate a new one to meet your specific requirements. Please contact the technical service department.

CHT Germany GmbH: Postfach 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany  
Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, Homepage: www.cht.com / www.cht-silicones.com