TECHNICAL DATA SHEET



24 mths

QGel 329 General purpose silicone gel

Description	Property	Test Method	Value
QGels are addition-cure clear, soft, moderately cross-linked silicone polymer. Silicone gels provide protection from moisture,	Uncured Product	wethou	
vibration, thermal, or mechanical shock.	Cure Profile		20 mins at 150°C, 60 mins at
Key FeaturesSoft, but resilient	Cure Type		100°C, 24 hrs at 25°C Addition
1:1 mix ratioDispensing equipment not necessary	Density A	BS ISO	0.97
Use and Cure Information		2781 BS ISO	
Important	Density B	2781	0.97
In order to achieve optimum performance, the same lot number of the A and B components should be used. Mixed lots may not	Gel Time at 25°C/77°F		1.5 hr
obtain the performance criteria listed on the TDS or Certificate of	Mix Ratio By Weight Rheology		1:1 Gel
Analysis	Viscosity A	Brookfield	
The "A" part of QGels contain the platinum catalyst; great care should be taken when using automated dispensing equipment to	Viscosity B	Brookfield	950 cP
not cross-contaminate systems.	Cured Product		
Mixing Both the "A" and "B" parts should be well stirred to ensure the	Color		Transparent
material is uniform. QGels should be mixed by weight. Once the	Max Working Temp		204 °C / 399 °F
components are mixed, the curing process begins. The gel time	Min Working Temp		-55 °C / -67 °F
of the mixed material is listed under the typical properties. Fast curing gels should be dispensed utilizing automated mix and dispensing equipment. In order to achieve optimum performance,	Penetration (19.5g Cone Weight) mm		5 - 10 mm
the same "A" and "B" side lot numbers should be used.	Storage		
De-Aeration	Max Storage Temperature		38 °C / 100 °F

De-Aeration

Air trapped during mixing should be removed to eliminate voids in the cured product. Vacuum de-airing may be necessary to

completely remove all entrapped air bubbles. To ensure proper de-airing, subject the mixed material to 29 inches of mercury.

Storage and Shelf-life

This product is best when used within 24 months from the date of manufacture, See product label and/or the CoA for specific "use by date". Product should be stored in its original, unopened container in an environment that does not exceed 38C (100F)

Shelf Life

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case, the properties required for the intended use should be checked for quality assurance reasons.

Revision Date 16 Sep 2021 Revision No 4 Download Date 23 Apr 2024

CHT Germany GmbH: Postfach 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany

Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, Homepage: www.cht.com / www.cht-silicones.com

The content set out in the technical data sheet does not contain information upon which you should rely. It is provided for general information purposes only and does not constitute a product specification. You must obtain professional or specialist advice before taking any action based on the information provided in the technical data sheet.

CHT make reasonable efforts to ensure that information set out in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or guarantees (whether express or implied) that information set out in the technical data sheet is complete, accurate, or up-to-date or that the product will be suitable for your requirements. You should carry out your own testing to determine the applicability of such information and whether the product will be suitable. CHT reserve the right to modify the technical data sheet at any time. The CHT technical service department is available to offer further information and advice and should it be needed to look at modifying current products or custom formulate a new one to meet your specific requirements. Please contact the technical service department.