

## AF1500 LV

### Silicone Antifoam 100% Active Low Viscosity

#### Introduction

This antifoam is a 100% active silicone based antifoam compound. It is particularly effective in suppressing foam in many non-aqueous systems e.g. lubricating oils and can be employed in certain highly dispersed aqueous products e.g. agrochemical flowable formulations.

#### Key Features

- High antifoam activity
- Suitable for non-aqueous processes
- Resistant to pH range 3 to 9
- Temperature resistance <70 °C

#### Use and Cure Information

##### Applications

This antifoam is applied to knock down as to prevent foam for the production of: Cooking oils, Lubricating oils, BTX Extraction (Sulpholane Process), Agrochemical flowable formulations, Distillation Textile printing Inks, varnishes & coatings

##### How to Use

It can be used either as supplied or diluted with suitable diluents to the desired concentration, depending on the characteristics of the system. The concentration required for good foam control depends on the process where it is employed. If there is no previous experience of a foam problem, it is generally suggested to start with a concentration of 50 ppm of active silicone and then to adjust the amount upwards or downwards in order to determine the most cost effective concentration.

#### Health and Safety:

Safety Data Sheets available on request.

#### Packaging:

CHT Antifoams are available in a variety of packaging and sizes including drums and IBC's. Please contact our sales department for more information.

Revision Date : 02/11/2017

Download Date : 12/08/2020

Property	Test Method	Value
% Silicone		100 %
% Solids		100 %
Appearance		Translucent Liquid
Base Fluid Viscosity cst		550 cst
Colour		Translucent
FDA	CFR (21) 177.2600	No
SG	BS ISO 2781	1.01
Silicone Yes/No		Yes
Viscosity A-Part mPas	Brookfield	550 mPas
<b>Storage</b>		
Max storage temperature °C		30 °C
Min storage temperature °C		5 °C
Shelf life		12 mths

The information and recommendations in this publication are to the best of our knowledge reliable. However, nothing herein is to be construed as warranty or representation. Users should make their own test to determine the applicability of such information or the suitability of any products for their own particular purposes. Statements concerning the user of the products described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is to be assumed. All values are typical and should not be accepted as a specification