

## SE2011 2 part encapsulation and potting silicone

### Description

This is a self-bonding 2-component, silicone elastomer system specially designed for electronic potting and encapsulation applications. It offers good protection against chemicals, environmental contamination, mechanical shock, vibration and impact damage. It can be employed in areas where low flammability is a prerequisite. The cured elastomer can be repaired. The component parts have relatively low viscosities and are readily mixed either by hand or machine.

This silicone elastomer has the benefit of developing chemical adhesion to a variety of substrates and is compatible with many sensitive substrates including copper, brass, steel, aluminium, FR4, and plastics making this an ideal option where fast curing and adhesion are needed without the use of a primer.

### Key Features

- Adhesive at room temperature
- Fast curing at room temperature
- Low viscosity
- UL recognised in file No. E334038

### Application

Junction box potting for solar / photovoltaic cells

### Use and Cure Information

The product is supplied as two components 'A' and 'B'. These components should be mixed together in the ratio by weight shown opposite. Mixing can be done by hand or by automated dispensing machine using a static mixer nozzle. A nozzle of at least 9 GXF type elements is recommended for uniform mixing of both components.

The dispensing machine mix ratios should be adjusted if mixing by volume and not weight. IMPORTANT the mixed components will cure in the nozzle so to preserve nozzles a continuous process is required or a change of nozzle after the task is completed. Complete mixing of each component is achieved within the first 50-60% of the nozzle.

### Mixing

Both the 'A' and 'B' parts should be well stirred to ensure the material is uniform and any settlement of the fillers have been remixed.

Place the required amount of 'A' and 'B' parts by weight at the mix ratio shown opposite, in a clean plastic or metal container of approximately 3 times their volume, and mix until the colour of the mixture is uniform. For best results, we recommend degassing. Degas by intermittent evacuation, the larger volume of the mixing vessel helps prevent overflow during this operation. In case of automatic dispensing with static mixing head, the two components should be degassed before processing. Recommended vacuum conditions are 30-50 mbar intermittently over 5-10 minutes. Cast the mixture either by gravity or pressure injection.

### Adhesion

Ensure all substrates are clean and free of surface contaminants. A Solvent degreaser is recommended for metallic substrates and Iso-propanol solvent is recommended for plastics and polycarbonates. A mechanical bond to the substrates will develop shortly after applying. A chemical bond will develop after 24 hours and maximum adhesion is reached after 7 days.

It is important to check the compatibility in preliminary tests if unknown substrates are used.

### Health & Safety

### Property

#### Uncured Product

Cure Type	
De-mould Time / Full Cure at 23°C/73°F	
Density A	BS ISO 2781
Density B	BS ISO 2781
Mix Ratio By Weight	
Pot Life mins at 23°C/73°F	
Rheology	
Self Bonding	
Viscosity A	Brookfield
Viscosity B	Brookfield
Viscosity Mixed	Brookfield

#### Cured Product

#### 7 days at 23+/-2°C and 50+/-5% humidity

CTE Volumetric ppm/°C		837 ppm/°C
Color		Black
Density	BS ISO 2781	1.08 g/cm3
Elongation at Break	ISO 37	270 %
Hardness Shore A	ASTM D 2240-95	23
Linear Coefficient of Thermal Expansion (ppm/°C)		279 ppm/°C
Linear Shrinkage (%)		2.8 %
Max Working Temp		220 °C / 428 °F
Min Working Temp		-50 °C / -58 °F
Tensile Strength	ISO 40	0.9 N/mm2 / 131 psi
Thermal Conductivity		0.2 W/mK
UL File No.		E334038

#### Electrical Properties

Dielectric Constant	ASTM D-150	3.28
Dielectric Strength kV/mm	ASTM D-149	23.4 kV/mm / 594 V/mil
Dissipation Factor	ASTM D-150	0.029
Volume Resistivity (Ohms cm)	ASTM D-257	1.09E+14 ohms cm

#### Storage

Max Storage Temperature	40 °C / 104 °F
Shelf Life	6 mths

### Test Method

### Value

#### Condensation

2 hrs

1.05

0.83

10:1

20 min mins

Liquid

Yes

4400 cP

100 cP

4000 cP

The content set out in the technical data sheet does not contain information upon which you should rely. It is provided for general information purposes only and does not constitute a product specification. You must obtain professional or specialist advice before taking any action based on the information provided in the technical data sheet.

CHT make reasonable efforts to ensure that information set out in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or guarantees (whether express or implied) that information set out in the technical data sheet is complete, accurate, or up-to-date or that the product will be suitable for your requirements. You should carry out your own testing to determine the applicability of such information and whether the product will be suitable. CHT reserve the right to modify the technical data sheet at any time.

The CHT technical service department is available to offer further information and advice and should it be needed to look at modifying current products or custom formulate a new one to meet your specific requirements. Please contact the technical service department.

CHT Germany GmbH: Postfach 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany  
Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, Homepage: www.cht.com / www.cht-silicones.com

## Health and Safety

Safety Data Sheets available on request.

## Packaging

CHT Encapsulants are available in a variety packaging including bulk containers. Please contact our sales department for more information.

Revision Date 27 Sep 2021  
Revision No 3  
Download Date 05 Dec 2021

---

The content set out in the technical data sheet does not contain information upon which you should rely. It is provided for general information purposes only and does not constitute a product specification. You must obtain professional or specialist advice before taking any action based on the information provided in the technical data sheet.

CHT make reasonable efforts to ensure that information set out in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or guarantees (whether express or implied) that information set out in the technical data sheet is complete, accurate, or up-to-date or that the product will be suitable for your requirements. You should carry out your own testing to determine the applicability of such information and whether the product will be suitable. CHT reserve the right to modify the technical data sheet at any time.

The CHT technical service department is available to offer further information and advice and should it be needed to look at modifying current products or custom formulate a new one to meet your specific requirements. Please contact the technical service department.

**CHT Germany GmbH:** Postfach 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany  
Telephone: 07071/154-0, Fax: 07071/154-290, Email: [info@cht.com](mailto:info@cht.com), Homepage: [www.cht.com](http://www.cht.com) / [www.cht-silicones.com](http://www.cht-silicones.com)