

CHT-BeauSil™ GEL 8187 EM Silicone Crosspolymer Emulsion as an ingredient for Personal Care

Description

Silicone elastomer gels are an important raw material for modern high-end cosmetic products such as BB creams, lipglosses, pencils, foundations, primers, soft focus and anti-aging face creams for an even matte finish.

Key Features

- Non-tacky, non-oily and smooth feel
- Minimal emulsifier requirement
- Matte finish
- Cold processing


Key Applications

- Color Cosmetic
- Sun Care
- Primer
- Facial Masks

Application

CHT-BeauSil™ GEL 8187 EM is a silicone elastomer specially designed to be formulated directly with the aqueous phase. CHT-BeauSil™ GEL 8187 EM can be formulated at low temperatures with minimal emulsifier required adding immediately improved perception in skin feel.

Structure of a Crosspolymer Gel



Health & Safety

Safety Data Sheet available on request.

Packaging

Drums. Contact our sales department for further information.

Revision Date 03 Nov 2022
Revision No 7
Download Date 16 Apr 2024

Property

Product

Appearance

INCI Name

Ionicity

MIT Free

Non-Volatile Content (%)

Ultralow cyclic content

Viscosity

Addition Rates

Dosage - 1

Dosage - 2

Dosage - 3

Solubility

Solubility - Almond oil

Solubility - Cetyl Dimethicone

Solubility - Dimethicone
350cst

Solubility - Ethanol

Solubility -
Ethylhexylcarbonate

Solubility - Glycerine

Solubility - IPM

Solubility - Isododecane

Solubility - Paraffin Oil

Solubility - Polysorbate-20

Solubility - Propylenglycol

Solubility - Water

Storage

Max Storage Temperature

Min Storage Temperature

Shelf Life

Test

Method

Value

Clear blue to slightly hazy gel

Dimethicone (and)
Polysilicone-11 (and) Decyl
Glucoside (and) Butylene
Glycol

Non-ionic

Yes

Approx. 44

Yes

Brookfield 250,000 cP

0.1 - 10.0% in Sun Care

0.3 - 15.0% in Color
Cosmetic and Skin Care

0.1 -3.0% in Facial mask

Insoluble

Insoluble

Insoluble

Insoluble

Insoluble

Miscible

Insoluble

Insoluble

Insoluble

Miscible

Miscible

Soluble

40 °C / 104 °F

4 °C / 39 °F

12 mths

The content set out in the technical data sheet does not contain information upon which you should rely. It is provided for general information purposes only and does not constitute a product specification. You must obtain professional or specialist advice before taking any action based on the information provided in the technical data sheet.

CHT make reasonable efforts to ensure that information set out in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or guarantees (whether express or implied) that information set out in the technical data sheet is complete, accurate, or up-to-date or that the product will be suitable for your requirements. You should carry out your own testing to determine the applicability of such information and whether the product will be suitable. CHT reserve the right to modify the technical data sheet at any time. The CHT technical service department is available to offer further information and advice and should it be needed to look at modifying current products or custom formulate a new one to meet your specific requirements. Please contact the technical service department.

CHT Germany GmbH: Postfach 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany

Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, Homepage: www.cht.com / www.cht-silicones.com