

AS1420

SILCOTHERM 1 Part flowable heat cured silicone adhesive sealant

Introduction

This is a heat cured, non-corrosive, neutral cure, 1-part, silicone adhesive sealant. It is one in a range of Addition cure products which are solvent free. It exhibits primerless adhesion to many substrates when cured at temperatures above 100°C. It cures to form a very tough resilient silicone elastomer. This product will not corrode copper or its alloys and is suitable for use with electronic components.

Key Features

- Fast cure with heat
- Excellent thermal conductivity
- Non-corrosive
- Tough protective rubber

Use and Cure Information

This product is a ready to use 1-Part system. It is recommended that liquid versions be thoroughly mixed prior to use, particularly thermally conductive products which are supplied in tubs or pails. Ensure that all surfaces of the substrate are clean and degreased. The work area should be free of contaminants such as organic compounds of sulphur, phosphorus, nitrogen and tin, which act as catalyst poisons.

The rate of cure will depend on how long it takes for the sealant to reach the required curing temperature. Small beads of 1 to 2mm diameter, used as formed-in-place gaskets, can be cured quickly with hot air guns e.g. paint stripper types. With larger sections of sealant or when using as an encapsulant, cure times will increase and the use of an oven will be needed. Increasing the temperature will reduce cure times and maximum cure temperature should not exceed 200°C. All times are based on the actual time in an air-circulating oven at the stated temperature. Note: Improved adhesion is achieved by post cure at 120 to 150°C for 1 to 2 hours.

“For pneumatic dispensing of 310 ml cartridges, the recommended pressure is 2.25 to 3.45 bar (40 to 50 psi). Dispensing pressure above the recommended limits may lead to gas bypassing the piston, causing spluttering at the nozzle and poor bead quality”

Health and Safety

Safety Data Sheets available on request.

Packaging

CHT Adhesives are available in a variety packaging including cartridges and bulk containers. Please contact our sales department for more information.

Revision Date : 02/11/2017

Download Date : 13/08/2020

Property

Uncured product

Appearance
Cure Type
FDA
Max Cure Mins @ 100 °C
Rheology
Self Bonding
Viscosity A-Part mPas

Test Method

CFR (21] 177.2600
Brookfield

Value

Grey viscous liquid
Addition
No
30 mins
Flowable
Yes
43000 mPas

Cured product

After 1 hour at 150°C

CTE Linear ppm/°C
CTE Volumetric ppm/°C
Colour
Duro Shore A
Elongation %
Linear Shrinkage %
Max Working Temp +°C
Min Working Temp - °C
SG
Tensile MPa
Thermal Conductivity W/mK
UL 94V-0

ASTM D 2240-95
ISO 37
AFS_1540B
BS ISO 2781
ISO 37

187 ppm/°C
562 ppm/°C
Grey
67
70 %
2 %
260 °C
-50 °C
2.06
3.1 MPa
1.38 W/mK
No

Storage

Max storage temperature °C
Min storage temperature °C
Shelf life

15 °C
-5 °C
6 mths

Electrical properties

Dielectric Constant @ 1kHz
Dielectric Strength kV/mm
Surface Resistivity ohms
Volume Resistivity ohms cm

ASTM D-150
ASTM D-149
ASTM D-257
ASTM D-257

6
22.5 kV/mm
1.3E+15 ohms
7.7E+15 ohms cm

The information and recommendations in this publication are to the best of our knowledge reliable. However, nothing herein is to be construed as warranty or representation. Users should make their own test to determine the applicability of such information or the suitability of any products for their own particular purposes. Statements concerning the user of the products described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is to be assumed. All values are typical and should not be accepted as a specification