

QGel 305 High Strength Silicone Gel

Description	Property	Test Method	Value
<p>QGels are addition-cure clear, soft, moderately cross-linked silicone polymer. Silicone gels provide protection from moisture, vibration, thermal, or mechanical shock.</p> <p>Key Features</p> <ul style="list-style-type: none"> • 1:1 mix ratio • Room temperature or heat cure • Dispensing equipment recommended • High Strength <p>Use and Cure Information</p> <p>Important</p> <p>In order to achieve optimum performance, the same lot number of the A and B components should be used. Mixed lots may not obtain the performance criteria listed on the TDS or Certificate of Analysis.</p> <p>The "A" part of QGels contain the platinum catalyst; great care should be taken when using automated dispensing equipment to not cross-contaminate systems.</p> <p>Mixing</p> <p>Both the "A" and "B" parts should be well stirred to ensure the material is uniform. QGels should be mixed by weight. Once the components are mixed, the curing process begins. The gel time of the mixed material is listed under the typical properties. Fast curing gels should be dispensed utilizing automated mix and dispensing equipment. In order to achieve optimum performance, the same "A" and "B" side lot numbers should be used.</p> <p>De-Aeration</p> <p>Air trapped during mixing should be removed to eliminate voids in the cured product. Vacuum de-airing may be necessary to completely remove all entrapped air bubbles. To ensure proper de-airing, subject the mixed material to 29 inches of mercury.</p> <p>Storage and Shelf-life</p> <p>This product is best when used within 24 months from the date of manufacture, See product label and/or the CoA for specific "use by date". Product should be stored in its original, unopened container in an environment that does not exceed 38C (100F)</p> <p>Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case, the properties required for the intended use should be checked for quality assurance reasons.</p>	<p>Uncured Product</p> <p>Color A Color B Gel Time at 25°C/77°F Specific Gravity A Specific Gravity B Viscosity A Viscosity B</p> <p>Cured Product 150C for 30 mins</p> <p>Adhesive Force Adhesiveness Hexane Extraction Solids Hexane Extraction Weight Loss Penetration (19.5g Cone Weight) mm Penetration (69.5g Cone Weight) mm</p>	<p>Brookfield Brookfield Brookfield Brookfield</p>	<p>Transparent Transparent Blue 45 min 0.99 0.97 2,100 cP 900 cP</p> <p>8.2 grams 0.14 mJ 82 % 18 % 4 mm 13 mm</p>

Revision Date 08 Dec 2021
Revision No 3
Download Date 20 Sep 2024