

## ALPA-SIL TD ANTIST. SH. A 12 2 part Silicone Moulding Rubber

Description	Property	Test Method	Value	
<p>Pourable, addition-curing, 2-part silicone rubber that cures at room temperature. This product is mainly used for making antistatic silicone printing pads. The cured rubber exhibits excellent physical and electrical properties. Fast and non-shrink cure at room temperature which can be accelerated considerably by the application of heat.</p> <p><b>Key Features</b></p> <ul style="list-style-type: none"> <li>• Easy 1:1 mix ratio</li> <li>• Antistatic properties</li> <li>• Pink or green options</li> <li>• For use as a printing pad elastomer</li> </ul> <p><b>Application</b></p> <p>Soft Silicone Elastomer with antistatic properties for Pad-Printing applications.</p> <p><b>Use and Cure Information</b></p> <p><b>Mixing</b></p> <p>Components A and B are mixed at a mass ratio of 1 : 1. The two components are thoroughly mixed either by hand or with an electric or pneumatic stirrer at low speed to avoid air from being dragged in and/or to avoid a temperature increase. Crosslinking is slowed down by reducing the temperature and accelerated by increasing it. The non-tacky time is about 8 – 12 hours.</p> <p><b>Inhibition of cure</b></p> <p>Great care must be taken when handling and mixing all addition cured silicone elastomer systems, ensuring that all the mixing tools (vessels and spatulas) are clean and constructed in materials which do not interfere with the curing mechanism. The cure of the rubber can be inhibited by the presence of compounds of nitrogen, sulphur, phosphorus and arsenic; organotin catalysts and PVC stabilizers; epoxy resin catalysts and even contact with materials containing certain of these substances e.g. moulding clays, sulphur vulcanised rubbers, condensation cure silicone rubbers, onion and garlic.</p> <p>These substances may impair or even completely prevent the curing behavior of addition crosslinking silicones typically indicated by tacky surfaces. Therefore, it is absolutely important to check the compatibility in preliminary tests if unknown substrates are used.</p> <p><b>Health &amp; Safety</b></p> <p>Please observe our safety data sheets and the safety remarks on our container labels when handling our products. The dangerous goods regulations and the accident prevention regulations of the professional associations must be particularly observed. Keep the EC safety data sheet of the applied product at hand since it provides you with useful instructions for the safe use and disposal of the product as well as for actions to be taken in case of accidents.</p> <p><b>Delivery Units</b></p> <p>Component A: 5 kg or 25 kg Component B: 5 kg or 25 kg Other container sizes upon demand.</p> <p><b>Storage</b></p> <p>Components A and B can be optimally processed for approx. 12 months if stored properly at temperatures below 30 °C and protected from frost in closed original containers.</p>	<p><b>Uncured Product</b></p> <p>Appearance</p> <p>Color A</p> <p>Cure Type</p> <p>De-mould Time / Full Cure at 23°C/73°F</p> <p>Mix Ratio By Weight</p> <p>Pot Life mins at 23°C/73°F</p> <p>Tack Free Time / Skin Formation at 23°C/73°F</p> <p>Viscosity A</p> <p>Viscosity B</p> <p>Viscosity Mixed</p>		<p><b>Pink or Green</b></p> <p><b>Translucent</b></p> <p><b>Addition</b></p> <p><b>12 hrs</b></p> <p><b>1:1</b></p> <p><b>60 - 90 mins</b></p> <p><b>10 - 12 hr</b></p> <p><b>8000 cP</b></p> <p><b>8000 cP</b></p> <p><b>8000 cP</b></p>	
		<p><b>Cured Product</b></p> <p>Color</p> <p>Hardness Shore A</p> <p>Linear Shrinkage (%)</p>		<p><b>Pink or Green</b></p> <p><b>12</b></p> <p><b>&lt; 0.1 %</b></p>
		<p><b>Storage</b></p> <p>Max Storage Temperature</p> <p>Shelf Life</p>		<p><b>30 °C / 86 °F</b></p> <p><b>12 mths</b></p>
			Brookfield	<b>8000 cP</b>
			Brookfield	<b>8000 cP</b>
			Brookfield	<b>8000 cP</b>
			DIN 53 505	<b>12</b>
				<b>&lt; 0.1 %</b>
				<b>30 °C / 86 °F</b>
				<b>12 mths</b>
Revision Date	29 Apr 2021			
Revision No	1			
Download Date	16 May 2022			