

ICM EM 60,000 NO NP 40% active emulsion of 60,000 cSt hydroxy terminated polydimethylsiloxane

Description	Property	Test Method	Value
This product is an industrial anionic polydimethylsiloxane emulsion	Product		
Key Features	Appearance		Milk White
<ul style="list-style-type: none"> High molecular weight Long Lasting Performs at low concentrations easily dispersed with water with minimal agitation 	Base Fluid Viscosity (cst)		60,000
Key Applications	Density	BS ISO 2781	0.98 g/cm ³
<ul style="list-style-type: none"> Release Agent Auto Care Extrusion Leather and Vinyl Care 	INCI Name		PDMS emulsion
Application	Ionicity		Anionic
ICM EM 60,000 NO NP is a 40% active emulsion of 60,000 cSt hydroxy terminated polydimethylsiloxane. The high molecular weight dimethicone emulsion demonstrates excellent dilution stability at very low concentrations and is chemically inert. This emulsion was developed as an effective release agent for a variety of applications. ICM EM 60,000 NO NP is free of nonylphenols.	Non-Volatile Content (%)		40
Use and Cure Information	Ultralow cyclic content		No
To optimize the dispersion of this emulsion into the final formulation, it is recommended to add it slowly at the end of the procedure at a temperature below 40 °C (104 °F) with continuous mixing or stirring.	pH		7.5
Health & Safety	Addition Rates		
Read product and safety data sheets before handling this product for physical and health hazard information. The safety data sheet is available from your CHT representative.	Dosage - 1		0.1-1.0%
Limitations	Storage		
This product is not intended for pharmaceutical use.	Max Storage Temperature		40 °C / 104 °F
	Min Storage Temperature		4 °C / 39 °F
	Packaging		40 lb. pails or 441 lb. drums
	Shelf Life		12 mths

Revision Date 21 Sep 2021
 Revision No 5
 Download Date 22 Mar 2023