

KÖRAFORM 97067 A 2 part casting compound

Description

Condensation crosslinking silicone casting compound for pad printing, shore A 6

Key Features

- 100:3 mix ratio
- Low viscosity
- Suited printing pad manufacture
- Shore A 6

Application

PAD printing

Use and Cure Information

Prior to processing thoroughly stir up KÖRAFORM 97067 A to homogeneously distribute possibly deposited fillers. To KÖRAFORM 97067 A KÖRAFORM B 128 K is added at a mixing ratio of 100 : 3 according to weight and then mixed with a spatula or stirrer until the compound is homogeneous.

With this mixing the potlife of 60 min starts where KÖRAFORM 97067 A must be processed (casting or brushing). Demoulding can be effected after 24 hours. For an absolutely bubble-free vulcanizate the mixed silicone gel must be degassed using vacuum prior to the casting process (5 min at the most at 10 – 20 mbar). The viscosity can be increased up to strength by adding up to 1 weight per cent KÖRAFORM TM C to the catalyzed compound. When casting critical grounds, e.g. glass, check the release behaviour with your own trials. A silicone-free release agent may have to be applied.

Property

Uncured Product

Color A
Cure Type
De-mould Time / Full Cure at 23°C/73°F
Mix Ratio By Weight
Pot Life mins at 23°C/73°F
Viscosity A
Viscosity B

Test Method

Brookfield
Brookfield

Value

brick red
Condensation
24 hrs
100:3
60 mins
5000 cP
14 cP

Cured Product

Color
Hardness Shore A
Linear Shrinkage (%)

DIN 53 505

Brick Red
6
0.5 %

Storage

Max Storage Temperature
Min Storage Temperature
Shelf Life

30 °C / 86 °F
5 °C / 41 °F
6 mths

Solvents and Cleaning Agents

For removing fresh mass KÖRASOLV GL must be applied. Residues in the stirring or casting vessel can be easily removed by letting them cure in order to scrape them off afterwards.

	KÖRAFORM 97067 A component A	KÖRAFORM B 128 K component B		
Colour	brick red	colourless		
Viscosity	5,000	14	mPa·s	Brookfield HBTD ¹⁾
Density		0.99	g/cm³	DIN 53 479 ¹⁾
	Mixture			
Mixing ratio	100 : 3		according to weight	
Mixing viscosity	16,000			
Potlife	60		min	
Demouldable after	24		hours	
	Vulcanizate			
Hardness shore A	6			DIN 53 505 ²⁾
Tensile strength	not stated		N/mm²	DIN 53 504 S 3 A ²⁾
Elongation at break	not stated		%	DIN 53 504 S 3 A ²⁾
Res. to further tearing	not stated		N/mm	ASTM D 624 Form B ²⁾
Linear shrinkage	0.5		%	after 7 days

¹ = Measured under standard climate DIN 50 014-23/50-2
² = Vulcanizate, measured after 7 days of storage at room temperature

Storage

KÖRAFORM 97067 A can be optimally processed for at least six months if being stored at 5 °C – 30 °C in tightly closed original containers. KÖRAFORM B 128 K can be optimally processed for at least six months if being stored at 5 °C – 30 °C in tightly closed original containers.

The content set out in the technical data sheet does not contain information upon which you should rely. It is provided for general information purposes only and does not constitute a product specification. You must obtain professional or specialist advice before taking any action based on the information provided in the technical data sheet.

CHT make reasonable efforts to ensure that information set out in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or guarantees (whether express or implied) that information set out in the technical data sheet is complete, accurate, or up-to-date or that the product will be suitable for your requirements. You should carry out your own testing to determine the applicability of such information and whether the product will be suitable. CHT reserve the right to modify the technical data sheet at any time. The CHT technical service department is available to offer further information and advice and should it be needed to look at modifying current products or custom formulate a new one to meet your specific requirements. Please contact the technical service department.

CHT Germany GmbH: Postfach 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany
Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, Homepage: www.cht.com / www.cht-silicones.com

Health & Safety

Safety

Please observe our EC safety data sheets and the safety remarks on our container labels when handling our products. The dangerous goods regulations and the accident prevention regulations of the professional associations must be particularly observed. Keep the EC safety data sheet of the applied product at hand since it provides you with useful instructions for the safe use and disposal of the product as well as for actions to be taken in case of accidents.

Delivery units

KÖRAFORM 97067 A:

22 kg hobbocks

20 kg pails

5 kg pails

KÖRAFORM B 128 K:

0.5 kg PE bottles

Revision Date 27 Mar 2024

Revision No 2

Download Date 25 Apr 2024

The content set out in the technical data sheet does not contain information upon which you should rely. It is provided for general information purposes only and does not constitute a product specification. You must obtain professional or specialist advice before taking any action based on the information provided in the technical data sheet. CHT make reasonable efforts to ensure that information set out in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or guarantees (whether express or implied) that information set out in the technical data sheet is complete, accurate, or up-to-date or that the product will be suitable for your requirements. You should carry out your own testing to determine the applicability of such information and whether the product will be suitable. CHT reserve the right to modify the technical data sheet at any time. The CHT technical service department is available to offer further information and advice and should it be needed to look at modifying current products or custom formulate a new one to meet your specific requirements. Please contact the technical service department.

CHT Germany GmbH: Postfach 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany
Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, Homepage: www.cht.com / www.cht-silicones.com