TECHNICAL DATA SHEET

QLE 1039
Coating

Description

This elastomer is designed for fabric, textile or cloth coating applications where a tough coating and excellent adhesion is needed.

Key Features

- 100% solids
- Long open time
- Excellent adhesion
- Tough, resilient coating

Application

Fabric, textiles and cloth coating applications

Use and Cure Information

Important

The "A" part of this elastomer contains the platinum catalyst; great care should be taken when using automated dispensing equipment to not cross-contaminate systems.

Mixing

Both the "A" and "B" parts should be well stirred to ensure the material is uniform. The elastomers should be mixed by weight. Once they are mixed, the curing process begins. The gel time of the mixed material is listed under the typical properties. Fast curing gels should be dispensed utilizing automated mix and dispensing equipment. In order to achieve optimum performance, the same "A" and "B" side lot number should be used.

De-Aeration

Air trapped during mixing should be removed to eliminate voids in the cured product. Vacuum de-airing may be necessary to completely remove all entrapped air bubbles. To ensure proper de-airing, subject the mixed material to 29 inches mercury.

Property	Test Method	Value
Uncured Product		
Color		**Blue**
Color A		**Translucent**
Color B		**Blue**
Cure Profile		**60 minutes at 150°C**
Cure Type		**Addition**
Gel Time at 25°C/77°F		**>24 hr**
Mix Ratio By Weight		**1:1**
Rheology		**Liquid**
Self Bonding		**Yes**
Specific Gravity A		**1.02**
Specific Gravity B		**1.02**
Viscosity A	Brookfield	**31,000 cP**
Viscosity B	Brookfield	**18,000 cP**
Viscosity Mixed	Brookfield	**25,000 cP**
Cured Product		
60 minutes at 150°C		
Elongation at Break	ISO 37	**180 %**
Hardness Shore A	ASTM D 2240-95	**44**
Tensile Strength	ISO 37	**5.52 N/mm2 / 800 psi**
Young's Modulus		**470 psi**

Storage and Self-life

This product is best when used within 24 months for the date of manufacture; see product label and/or the CoA for the specific "use by date". Product should be stored in its original. unopened container in an environment that does niot exceed 38°C (100°F). Storage beyond the date specified on the label does not neccessarily mean that the product is no longer usable. In this case, the properties required for the intended use should be checked for quality assurance reasons.

Health & Safety

Please observe our safety data sheets and the safety remarks on our container labels when handling our products. The dangerous goods regulations and the accident prevention regulations of the professional associations must be particularly observed. Keep the safety data sheet of the applied product at hand since it provides you with useful instructions for the safe use and disposal of the product as well as for actions to be taken in case of accidents.

Revision Date	29 Sep 2021
Revision No	3
Download Date	07 Sep 2026

The content set out in the technical data sheet does not contain information upon which you should rely. It is provided for general information purposes only and does not constitute a product specification. You must obtain professional or specialist advice before taking any action based on the information provided in the technical data sheet.
CHT make reasonable efforts to ensure that information set out in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or guarantees (whether express or implied) that information set out in the technical data sheet is complete, accurate, or up-to-date or that the product will be suitable for your requirements. You should carry out your own testing to determine the applicability of such information and whether the product will be suitable. CHT reserve the right to modify the technical data sheet at any time. The CHT technical service department is available to offer further information and advice and should it be needed to look at modifying current products or custom formulate a new one to meet your specific requirements. Please contact the technical service department.
CHT Germany GmbH: Postfach 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany
Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, Homepage: www.cht.com / www.cht-silicones.com