

QM Pt Accelerator Addition cure curing accelerator

Description	Property	Test Method	Value
<p>This can be used with two-component, room temperature, addition cure, silicone materials to reduce the de-mold time. When added at 1% to the silicone base, it will reduce the de-mold time by roughly one half. The work time will also be significantly reduced.</p> <p>This product can also be used as a surface treatment to prevent inhibition.</p>	Uncured Product		Clear
	Color		Addition
<p>Key Features</p> <ul style="list-style-type: none"> • Reduces de-mold time • Low Viscosity • Casting resin resistance • Inhibition resistance 	Cure Type		Liquid
	Rheology		0.97
	Specific Gravity	Brookfield	2,200 cP
	Viscosity		
<p>Use and Cure Information</p> <p>The applications for this are numerous and varied. All application methods and recommended levels must be considered on an individual basis. Contact the CHT USA customer service team or your sales representative for details.</p>	Storage		
	Max Storage Temperature		38 °C / 100 °F
	Shelf Life		24 mths

Health & Safety

Safety Data Sheets available on request.

Revision Date 14 Oct 2021
 Revision No 4
 Download Date 13 Aug 2022