

QSil 440 2 part encapsulation and potting silicone

Key Features

- 100% solids
- Fast curing
- Low modulus
- Primerless adhesion to a variety of substrates

Revision Date 29 Apr 2021
Revision No 1
Download Date 13 Aug 2022

Property	Test Method	Value
Uncured Product		
Cure Profile		24 hours at 25°C
Cure Type		Condensation
Density A	BS ISO 2781	1.5
Density B	BS ISO 2781	0.97
Gel Time at 25°C/77°F		5 min
Mix Ratio By Weight		100:8
Rheology		Liquid
Viscosity Mixed	Brookfield	160000 cP
Cured Product		
Color		White
Hardness Shore A	ASTM D 2240-95	45
Max Working Temp		204 °C / 399 °F
Min Working Temp		-55 °C / -67 °F
Storage		
Max Storage Temperature		38 °C / 100 °F
Shelf Life		12 mths

The content set out in the technical data sheet does not contain information upon which you should rely. It is provided for general information purposes only and does not constitute a product specification. You must obtain professional or specialist advice before taking any action based on the information provided in the technical data sheet. CHT make reasonable efforts to ensure that information set out in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or guarantees (whether express or implied) that information set out in the technical data sheet is complete, accurate, or up-to-date or that the product will be suitable for your requirements. You should carry out your own testing to determine the applicability of such information and whether the product will be suitable. CHT reserve the right to modify the technical data sheet at any time. The CHT technical service department is available to offer further information and advice and should it be needed to look at modifying current products or custom formulate a new one to meet your specific requirements. Please contact the technical service department.

CHT Germany GmbH: Postfach 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany
Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, Homepage: www.cht.com / www.cht-silicones.com