

QSiil 6101 Condensation cure for potting applications

Description	Property	Test Method	Value
PRODUCT DESCRIPTION QSiil 6101 is a 100% silicone solids elastomer designed for electrical potting applications. The two-component system offers quick curing, a low modulus, and is a self-bonding material. This material also has good primerless adhesion to a variety of substrates.	Uncured Product		
	Cure Profile		24 hrs at 25°C
Key Features <ul style="list-style-type: none"> • 100% solids • Fast curing, low viscosity, very flowable • Excellent adhesion to many substrates including polycarbonate, PPO/PS & PPE/PS • UL listed in file No. E205830, meets UL requirements for solar J-box potting Application Solar panel / photovoltaic cell junction box potting	Cure Type		Condensation
	Density A	BS ISO 2781	1.21
	Density B	BS ISO 2781	0.96
	Gel Time at 25°C/77°F		4 min
	Mix Ratio By Weight		100:8
	Rheology		Liquid
	Viscosity Mixed	Brookfield	6000 cP
	Cured Product		
	Color		Black
	Hardness Shore A	ASTM D 2240-95	30
UL File No.		E205830	
Electrical Properties Comparative Tracking Index (volts)			>600 volts
	Adhesion Testing		
Lap Shear Adhesive Strength on Polycarbonate (lbf)			71 lbf
Storage Max Storage Temperature Shelf Life			38 °C / 100 °F
			12 mths

UNCATAYLZED		
PROPERTY	QSil 6101	QSil Cat 6101
Appearance	Black	Clear
Viscosity	6,700 cps	30 cps
Specific Gravity	1.21	0.96

CATALYZED 24 hours at 25 °C	
MIX RATIO 100:8 by weight, 10:1 by volume	
PROPERTY	RESULT
Gel Time at 25 °C *	4 minutes
Durometer	30, Shore A
Adhesion	
Aluminum	Cohesive Failure
Polycarbonate	Cohesive Failure
PPE/PS Blends	Cohesive Failure
PPO/PS Blends	Cohesive Failure
Lap Shear (polycarbonate/polycarbonate)	
12H at RT	62 lbf
24H at RT	65 lbf
72H at RT	71 lbf
168H at 85 °C/85%RH	62 lbf
1,000H at 85 °C/85RH	60 lbf
Minimum Cure Time to 100% Cohesive Failure	
Aluminum	6 hours
Polycarbonate	16 hours
PPE/PS Blends	24 hours
PPO/PS Blends	3 hours

* Gel time is defined as the time required for the material to become a solid or a semi-solid

UL Results at 3mm (File E205830)	
UL 94	V-1
HAI	1
HWI	3
CTI	0

ADHESION

Ensure the surface is clean and free of any foreign substances. Clean the surface of the substrate to be adhered to with a suitable solvent for best results. MIXING In order to achieve optimum performance, the same lot number of QSil 6101 and QSil Cat 6101 should be used. QSil 6101 should be thoroughly mixed prior to use.

Mixing by hand: Mixing by hand is not recommended for this product. If mixing by hand, QSil 6101 is catalyzed with QSil Cat 6101 at a mix ratio of 100:8 by weight. The volume of the container should be 3 – 4 times the volume of the material to be mixed. Accurate weighing of all components, on a suitable scale, is essential for optimal product performance when mixing by hand. Mixing and dispensing with automatic equipment: QSil 6101 is catalyzed with QSil Cat 6101 at a 10:1 ratio by volume. Use a system that will properly mix the A and B components. CHT USA has identified cartridges and static mixers that work extremely well with this material. Please contact your customer service representative for information on 400 ml cartridges as well as for the appropriate static mixers. This material can be easily machine dispensed and CHT USA has demonstrated this in conjunction with Graco. QSil 6101 can be readily dispensed through a PR-70V with excellent mixing with the appropriate static mixer. There are additional equipment suppliers who can also provide pumps that will adequately mix QSil 6101. Contact your sales or customer service representative for additional information.

DE-AERATION

Machine mixed material does not normally need to be de-aired.

STORAGE See product label and/or CoA for specific "Use By Date". Product should be stored in its original, unopened container. Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case, the properties required for the intended use should be checked for quality assurance reasons.

Revision Date 29 Apr 2021

The content set out in the technical data sheet does not contain information upon which you should rely. It is provided for general information purposes only and does not constitute a product specification. You must obtain professional or specialist advice before taking any action based on the information provided in the technical data sheet.

CHT make reasonable efforts to ensure that information set out in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or guarantees (whether express or implied) that information set out in the technical data sheet is complete, accurate, or up-to-date or that the product will be suitable for your requirements. You should carry out your own testing to determine the applicability of such information and whether the product will be suitable. CHT reserve the right to modify the technical data sheet at any time. The CHT technical service department is available to offer further information and advice and should it be needed to look at modifying current products or custom formulate a new one to meet your specific requirements. Please contact the technical service department.

CHT Germany GmbH: Postfach 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany
Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, Homepage: www.cht.com / www.cht-silicones.com

Revision No 1
Download Date 03 Jul 2024

The content set out in the technical data sheet does not contain information upon which you should rely. It is provided for general information purposes only and does not constitute a product specification. You must obtain professional or specialist advice before taking any action based on the information provided in the technical data sheet.

CHT make reasonable efforts to ensure that information set out in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or guarantees (whether express or implied) that information set out in the technical data sheet is complete, accurate, or up-to-date or that the product will be suitable for your requirements. You should carry out your own testing to determine the applicability of such information and whether the product will be suitable. CHT reserve the right to modify the technical data sheet at any time. The CHT technical service department is available to offer further information and advice and should it be needed to look at modifying current products or custom formulate a new one to meet your specific requirements. Please contact the technical service department.

CHT Germany GmbH: Postfach 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany
Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, Homepage: www.cht.com / www.cht-silicones.com