

QSil Primer No. 3UV Primer-Silicone Adhesion Aid

Description

The primer is a complex solution of reactive silanes in a volatile solvent. Upon application, the carrier solvent evaporates leaving behind a layer amenable to bonding various silicone elastomers. An appropriate combination of primer and application procedure can yield a bonding layer capable of adhering silicone to a variety of substrates. Primers typically enable adhesion at relatively low temperature.

Key Features

- Works with condensation and addition cure materials
- Adhesion to metals, rubbers, polyester and nylon
- Contains a UV tracer
- One-component, carried in odorless mineral spirits

Application

QSil Primer #3UV is for use with condensation and addition cure silicone elastomers.

Use and Cure Information

Surfaces to be bonded should be dry and free from grease, oil, dust, and release agents. Non-porous substrates should be solvent degreased prior to application of the primer.

The primer formulations can be applied to a substrate via a variety of methods. Suggestions include: wiping with a lint-free cloth, painting with a brush, dipping the substrate in a bath of primer, and spraying. The appropriate cured primer film thickness is dependent on the substrate and application. Film thicknesses ranging from a few hundred nanometers up to approximately 12 microns (0.5 mil) are typical. In the case of Pt-cure systems, a primer can form a protective layer that prevents inhibition.

The end user should establish the appropriate process parameters for their specific application. The active ingredients require moisture to cure and should be in an environment having relative humidity greater than 40%. The primer should be allowed to cure for approximately 30 minutes prior to application of the silicone. The cure may be accelerated with modest heating, such as 50 °C for 10 minutes. If maintained contaminate-free, primed parts can be used from a few to several hours later—it is suggested that the end user establish these parameters in the context of their application.

Health & Safety

The primer contains solvents which are classified as hazardous under current regulations. Please observe the safety data sheets and the safety statements on the container labels when handling our products. The dangerous goods regulations and the accident prevention regulations of the professional associations must be particularly observed. Keep the safety data sheet of the applied product at hand since it provides useful instructions for the safe use and disposal of the product as well as for actions to be taken in case of accidents.

Revision Date 11 Nov 2021
Revision No 6
Download Date 14 Nov 2024

Property	Test Method	Value
Product		
Solids Content (%)		10 %
Uncured Product		
Appearance		Blue tint
Color		Opaque white, fluorescent in UV light
Cure Profile		>40% humidity
Cure Type		Condensation
Flash Point °C	BS 2000-34	40 °C
Rheology		Liquid
Specific Gravity		0.82
Tack Free Time / Skin Formation at 23°C/73°F		30 min
UV Trace		Yes
Storage		
Max Storage Temperature		38 °C / 100 °F
Shelf Life		24 mths

The content set out in the technical data sheet does not contain information upon which you should rely. It is provided for general information purposes only and does not constitute a product specification. You must obtain professional or specialist advice before taking any action based on the information provided in the technical data sheet. CHT make reasonable efforts to ensure that information set out in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or guarantees (whether express or implied) that information set out in the technical data sheet is complete, accurate, or up-to-date or that the product will be suitable for your requirements. You should carry out your own testing to determine the applicability of such information and whether the product will be suitable. CHT reserve the right to modify the technical data sheet at any time. The CHT technical service department is available to offer further information and advice and should it be needed to look at modifying current products or custom formulate a new one to meet your specific requirements. Please contact the technical service department.

CHT Germany GmbH: Postfach 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany
Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, Homepage: www.cht.com / www.cht-silicones.com