

SiIso CONNECT 21000 2 part heat curing silicone elastomer - electrically conductive

Description	Property	Test Method	Value
Uncured Product			
This is a two component silicone elastomer which crosslinks through polyaddition reaction. Particularly well suited for LSR applications and when processing with injection moulding equipment.	Color A		black
{{additional_data}}	Color B		black
Key Features	Cure Profile		1 hour at 100 - 130°C
• Electrically conductive	Cure Type		Addition
• Non-corrosive	Density A	BS ISO 2781	1.1
• Heat curing	Density B	BS ISO 2781	1.1
• Low linear shrinkage	Mix Ratio By Weight		1:1
Application	Pot Life mins at 23°C/73°F		>1440 mins
Smart textiles. Pressure sensors, RFI gaskets and shielding - application by coating or liquid injection moulding	Rheology		Viscous liquid
Use and Cure Information	Viscosity A	Brookfield	71000 cP
Mix components A and B in accordance with the mix ratio shown opposite according to weight. The material is usually processed with liquid injection moulding machines.	Viscosity B	Brookfield	75000 cP
Crosslinking and the speed of cure can be controlled by reducing the temperature to slow down the reaction or increasing the temperature to speed it up.	Cured Product		
A detailed rheometer report can be made available upon request.	Color		Black
Inhibition of the cure	Elongation at Break	ISO 37	240 %
Certain substances may impair or even completely prevent the curing behaviour of addition crosslinking silicone. Typical indications are sticky surfaces between silicone and contact surfaces.	Hardness Shore A	DIN 53 505	35
The following substances are particularly critical:	Tear Resistance (N/mm)	BS ISO 34-1	5.5 N/mm / 31 ppi
• substances containing nitrogen (amines, polyurethanes, epoxy resins)	Tensile Strength	ISO 37	1.9 N/mm² / 276 psi
• substances containing sulphur (polysulphides, polysulphones, natural and synthetic rubbers (EPDM))	Thermal Conductivity		0.35 W/mK
• organometal compounds (organotin compounds, vulcanisates and hardeners of condensation crosslinking silicones)	Electrical Properties		
{{provisional_how_to_use}}	Volume Resistivity (Ohms cm)	ASTM D-257	<1E+3 ohms cm
Health & Safety	Storage		
Please observe our EC safety data sheets and the safety remarks on our container labels when handling our products. The dangerous goods regulations and the accident prevention regulations of the professional associations must be particularly observed. Keep the EC safety data sheet of the applied product at hand since it provides you with useful instructions for the safe use and disposal of the product as well as for actions to be taken in case of accidents	Max Storage Temperature		30 °C / 86 °F
Safety Data Sheets available on request.	Shelf Life		6 mths

Revision Date 21 Oct 2021
Revision No 4
Download Date 03 Jul 2024